



Ninth Avenue East, Team Valley Trading Estate, Gateshead,
Tyne & Wear NE11 0EJ England
Telephone: 0191 4914433
FAX: 0191 4872504

圓型管件固持劑

R62 耐高溫至 232

技術資料

描述

R62 是一種綠色中高黏度之厭氧硬化之壓克力圓形管
件固持膠，可耐高溫至 232 並具高強度，使用時可搭
配促進劑 A471。

應用

本產品固定效果快速，強度佳，適用於須耐高溫 150
以上之管件固持。

使用注意事項

清潔欲接著材質表面，儘量使欲固定螺絲密和。
欲加快本產品之固持速度可於塗膠後將工件送入烤箱
100 30 分鐘或是塗膠前先將工件加熱至 100 ，都可
加快固化速度。

操作指示

確認接著之零件為乾燥及清潔

物性

樹脂.....	變性甲基丙烯酸脂
顏色.....	綠色
初步固持速度（無促進劑）	<15 分
黏度	7,000 cps
填縫性.....	0.2mm
閃火點.....	>85°C
保存期限.....	12 月 @ 25°C
比重.....	1.04 g/cm ³
可使用溫度範圍:.....	-55°C to + 232°C

硬化後特性

完全硬化時間.....	24 hours
鬆脫扭矩....	20 N/mm ²

保存

本產品之貯存應勿直接被陽光照射
保存期限: 12 月 @ 25°C. 確保已開罐之產
品勿置於紫外線之照射

安全及衛生

本產品不含壓克力酸
刺激物: 本產品含甲基丙烯酸脂，可能對眼睛及
呼吸器官具有刺激性，亦可能刺激皮膚，如有
皮膚刺激現象，須立即施以大量清水衝洗
CONSULT HSS 182

The information contained herein is produced in good faith and is believed to be reliable but is for guidance only. Holdtite and its agents cannot assume liability or responsibility for results obtained in the use of its products by persons whose methods are outside or beyond our control. It is the users responsibility to determine the suitability of any of the products and methods of use or preparation prior to use mentioned in our literature and furthermore the users responsibility to observe and adopt such precautions as may be advisable for the protection of personnel and property in the handling and use of any of our products.