



Ninth Avenue East, Team Valley Trading Estate, Gateshead,
Tyne & Wear NE11 0EJ England
Telephone:0191 4914433
FAX:0191 4872504

螺絲固定劑

THREADLOCKER T22

技術資料

描述

Threadlocker T22 是一種紫色低等黏度之厭氧硬化之壓克力螺絲固定膠，使用時可搭配促進劑 A471。

應用

本產品具排油性，可使用於含油膜之工作物表面，固定效果快速，即使不活化金屬工作物，亦可藉由本產品之厭氧特性，獲至良好固定效果。

使用注意事項

清潔欲接著材質表面，儘量使欲固定螺絲密和。

特性

當溫度保持在 150 時其強度仍有 50%
填縫性最低可至 0.2mm

操作指示

確認接著之零件為乾燥及清潔

物性

樹脂.....	變性甲基丙烯酸脂
顏色.....	紫色
初步固持速度 (無促進劑)	15 分
黏度	1200 cps
填縫性.....	0.2mm
閃火點.....	>85°C
保存期限.....	12 月 @ 25°C
比重.....	1.04 g/cm ³
可使用溫度範圍:.....	-55°C to + 150°C

硬化後特性

完全硬化時間.....	24 hours
鬆脫扭矩....	6 N/mm ²
磨擦扭矩....	4 N/mm ²

保存

本產品之貯存應勿直接被陽光照射
保存期限: 12 月 @ 25°C. 確保已開罐之產品勿置於紫外線之照射

安全及衛生

本產品不含壓克力酸
刺激物: 本產品含甲基丙烯酸脂, 可能對眼睛及呼吸器官具有刺激性, 亦可能刺激皮膚, 如有皮膚刺激現象, 須立即施以大量清水衝洗
CONSULT HSS 182

The information contained herein is produced in good faith and is believed to be reliable but is for guidance only. Holdtite and its agents cannot assume liability or responsibility for results obtained in the use of its products by persons whose methods are outside or beyond our control. It is the users responsibility to determine the suitability of any of the products and methods of use or preparation prior to use mentioned in our literature and furthermore the users responsibility to observe and adopt such precautions as may be advisable for the protection of personnel and property in the handling and use of any of our products.